

IKO base V3 T/T 10 m

01211311

Description:

Underlayer composed of polymer bitumen and a glass fibre fleece inlay. The upper surface of this underlay is finished with a thermofusible film and the lower surface is protected by sand.

Installation

Installation: bonded with bituminous cold glue, with hot bitumen, torched-on or loosely laid and ballasted

Composition

| | |
|----------------------|--|
| Type of bitumen | Polymeric |
| Upper surface finish | Sand |
| Inlay | Glass fibre fleece 60 g/m ² |
| Lower surface finish | Sand |

Technical characteristics:

| | |
|--|--------|
| Tensile strength L (EN 12311-1 MDV N/50 mm +/- 20%) | ≥150 |
| Tensile strength T (EN 12311-1 MDV N/50 mm +/- 20%) | ≥150 |
| Elongation L (EN 12311-1 MDV % +/- 15% abs.) | NPD |
| Elongation B (EN 12311-1 MDV % +/- 15% abs.) | NPD |
| Nail tear resistance(EN 12310-1 MDV N Only MF) | NPD |
| Flexibility at low temperature (EN 1109 MLV °C Surface/Bottom) | ≤-3 |
| Flow temperature (EN 1110) | ≥90 |
| Shear resistance (EN 12317-1 MDV N/50 mm) | NPD |
| Dimensional stability (EN 1107-1 MLV) | NPD |
| Fire resistance | Proof |
| Vapour diffusion resistance (μd) | ≥ 30 m |
| Root resistant (EN 13948) | - |

Packaging:

| | |
|--------------------------|----------------------------|
| Nominal thickness (mm) | 3 |
| Thickness tolerance (mm) | +/- 0,2 |
| Length (m) | 10 |
| Width (m) | 1 |
| Width of overlap (cm) | - |
| Weight per roll(kg) | +/- 43 |
| Number of rolls / pallet | 25 |
| Type of pallet | 1 x 1,2 m guarantee pallet |

Certificates:

- BENOR
- Production ISO 9001 & 14001

IKO hereby certifies that this construction product complies with the provisions of the following European Directive(s) if installed in accordance with the system directions and installation rules set out in the documentation:

- Council Directive 89/106/EEC on Construction Products
- EN 13707

FPC certificate obtained from SGS Notified Body, registered under registration number 0958.

Certificate number: 0958-CPR-2009/1.

