

## IKO base V4 F/T 10 m

01212421

### Description:

Underlayer composed of polymer bitumen and a glass fibre fleece inlay. The upper surface of this underlay is finished with a thermofusible film and the lower surface is protected by sand.

### Installation

Installation: bonded with bituminous cold glue, with hot bitumen, torched-on or loosely laid and ballasted

### Composition

Type of bitumen	Polymeric
Upper surface finish	Thermofusible film
Inlay	Glass fibre fleece 60 g/m <sup>2</sup>
Lower surface finish	Sand

### Technical characteristics:

Tensile strength L (EN 12311-1 MDV N/50 mm +/- 20%)	≥150
Tensile strength T (EN 12311-1 MDV N/50 mm +/- 20%)	≥150
Elongation L (EN 12311-1 MDV % +/- 15% abs.)	NPD
Elongation B (EN 12311-1 MDV % +/- 15% abs.)	NPD
Nail tear resistance(EN 12310-1 MDV N Only MF)	NPD
Flexibility at low temperature (EN 1109 MLV °C Surface/Bottom)	≤-3
Flow temperature (EN 1110)	≥90
Shear resistance (EN 12317-1 MDV N/50 mm)	NPD
Dimensional stability (EN 1107-1 MLV)	NPD
Fire resistance	Proof
Vapour diffusion resistance (μd)	≥ 40 m
Root resistant (EN 13948)	-

### Packaging:

Nominal thickness (mm)	4,0
Thickness tolerance (mm)	+/- 0,2
Length (m)	10
Width (m)	1
Width of overlap (cm)	-
Weight per roll(kg)	+/- 52
Number of rolls / pallet	20
Type of pallet	1 x 1,2 m guarantee pallet

### Certificates:

- BENOR
- Production ISO 9001 & 14001

IKO hereby certifies that this construction product complies with the provisions of the following European Directive(s) if installed in accordance with the system directions and installation rules set out in the documentation:

- Council Directive 89/106/EEC on Construction Products
- EN 13707

FPC certificate obtained from SGS Notified Body, registered under registration number 0958.

Certificate number: 0958-CPR-2009/1.

