

Metaprim

Description:

Metaprim is a two-component primer based on methacrylates.

Metaprim cures by adding the appropriate amount of catalyst (Metatec Catalyst).

Use:

Metaprim is used as primer for the liquid waterproofing systems Metatec Roof, Metatec Detail and Metatec BTG on mineral substrates, like concrete and cementitious substrates.

Colour:

White

Packaging:

Metaprim: 10kg metal tin (item number 02411001)

Metatec Catalyst: 100g plastic bag (item number 00095110)

Metaprim is delivered without Metatec Catalyst.

Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

Certificates:

Production ISO 9001 & 14001



Technical characteristics:

Dry substance +/- 56%

Density +/- 1,06 g/cm³

Viscosity +/- 500 mPas (25°C, 100 rpm, spindle 3)

Mixing ratio and instructions:

Anschließend Metatec Catalyst unter laufendem Rührwerk zugeben und 2 Min. homogen mit einer maschinell bei langsamen Geschwindigkeit mischen. Achten Sie darauf, dass die Masse am Boden und Rand des Behälters mit erfasst wird.

Die Dosierung von Metatec Catalyst basiert auf 10 kg Metaprim ist der Untergrundtemperatur abhängig:

- +3°C till +10°C 0,6kg Metatec Catalyst
- +10°C till +20°C 0,4 kg Metatec Catalyst
- +20°C till +35°C 0,2 kg Metatec Catalyst
- +35°C till +50°C 0,1 kg Metatec Catalyst
- The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

Curing time:

Pot life +/- 15 min

Rain-proof +/- 30 min

Can be walked on +/- 45 min

Fully cured +/- 2 h

Application:

Air temperature 3°C - 35°C

Substrate temperature 3°C - 50°C

Product temperature 3°C - 30°C

Consumption rate:

0,4 - 0,8 kg/m²

Cleaning of tools:

Butyl- oder Ethylacetat

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations. and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from www.ikoprotect.com.