

## Metaprim Detail

### Description:

Metaprim Detail is a two-component primer based on methacrylates.

Metaprim Detail cures by adding the appropriate amount of catalyst (Metatec Catalyst).

### Use:

Metaprim Detail is used as primer for the liquid waterproofing systems Metatec Roof, Metatec Detail and Metatec BTG on bitumen roof felt, singly ply membranes and asphalt.

### Colour:

Transparent

### Packaging:

Metaprim Detail: 10kg metal tin (item number 02411010)

Metatec Catalyst: 100g plastic bag (item number 00095110)

Metaprim Detail is delivered without Metatec Catalyst.

### Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

### Certificates:

Production ISO 9001 & 14001



### Technical characteristics:

Dry substance +/- 52%

Density +/- 1,02 g/cm<sup>3</sup>

Viscosity +/- 32 sec (25°C, Flowcup 6mm)

### Mixing ratio and instructions:

First stir the content of the tin mechanically at the low-speed setting. Add the Metatec Catalyst while stirring and mix mechanically and homogeneously at the low-speed setting during 2 minutes. Make sure that the product at the base and at the edge of the tin is properly mixed in.

The required amount of Metatec Catalyst for 10kg Metaprim Detail depends on the temperature of the substrate:

- -5°C till +10°C 0,6kg Metatec Catalyst
- +10°C till +15°C 0,4 kg Metatec Catalyst
- +15°C till +30°C 0,3 kg Metatec Catalyst
- +30°C till +40°C 0,2 kg Metatec Catalyst
- +40°C till +50°C 0,1 kg Metatec Catalyst

The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

### Curing time:

Pot life +/- 15 min

Rain-proof +/- 30 min

Can be walked on +/- 45 min

Fully cured +/- 3 h

### Application:

Air temperature -5°C - 35°C

Substrate temperature 3°C - 50°C

Product temperature 3°C - 30°C

### Consumption rate:

0,4 - 0,8 kg/m<sup>2</sup>

### Cleaning of tools:

ethyl acetate or butyl acetate

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from [www.ikoprotect.com](http://www.ikoprotect.com).