

IKO PRO REFRESH ASPHALT

Description:

- Semi-liquid thixotropic product based on bituminous emulsion, resins and fillers.

Use:

- Renovation of weathered asphalt layers.
- Preventing the asphalt layer against loose come stones.
- Protection and sealing in case of an asphalt layer that is not enough condense.
- Sealing of small cracks.
- Prevention of frost damage.

Characteristics:

- None-skid covering.
- Flexible covering.
- Good resistance on temperature fluctuations.
- Contains no solvent.

Caracteristics:

- Colour: black
- Density: +/- 1.2
- Viscosity at 25°C Brookfield RVT-spindle 6-20 t/min : +/- 7.000 cps
- Dry time at 20°C RH 50-60%
 - Hand-dry : after +/- 8 hours
 - Hard: after +/- 24 hours
- Dry contents - by weight: 62-68 %

Consumption rate:

- +/- 0.8 kg/m². Maximum 1 kg/m².

Cleaning tools and stains:

- Immediately with water.

Implementation:

- The surface must be free from loose particles, grease and oil.
- Don't apply on a substrate that is treat with coal tar product.
- Repair wells with **IKOpro Tinascoat** or **Asco Rephalt** before treatment. Wait minimum 3 weeks after reparation of wells before placing **IKOpro Refresh Asphalt**.
- Mix **IKOpro Refresh Asphalt** before use.
- Spread the product on the surface with a rubber swapper or a soft brush.
- On a new asphalt layer put **IKOpro Refresh Asphalt** on the surface when the layer is still tepid.
- The temperature of the surface must be between 10°C and 30°C. Ideal temperature between 15°C and 20 °C.

Storage:

- 6 months protected from frost, in airtight packaging.

Packaging:

- Pails of 20 kg.