

# IKO polyester Fleece 110P

## Characteristics:

---

- Non-woven polyester and polypropylene reinforcing fleece with a density of 110 g/m<sup>2</sup>
- Contains micro-perforations for a quick saturation
- Provided with a printed grid of 5cm by 5cm rectangles to facilitate the cutting of the fleece
- High tear and shear resistance
- Thickness control function when applying the first layer of the waterproofing membrane
- Production ISO9001 & 14001

## Use:

---

IKO polyester Fleece 110P is used as reinforcing fleece in the following liquid waterproofing systems:

- IKO hybritech Roof
- IKO hybritech Detail
- IKO metatech Roof
- IKO metatech Detail
- IKO metatech Balcony
- IKO metatech Car Park

## Technical characteristics:

---

Tensile strength MD	> 120 N/5cm
Tensile strength CD	> 150 N/5cm
% Elongation MD	> 50%
% Elongation CD	>60%

## Sizing and palletization:

---

Roll of 1,05m x 50m (item nummer 05225731)

Roll of 0,7m x 50m (item number 05225732)

Roll of 0,5m x 50m (item number 05225733)

Roll of 0,35m x 50m (item number 05225734)

Roll of 0,25m x 50m (item number 05225735)

Roll of 0,2m x 50m (item number 05225736)

Roll of 0,15m x 50m (item number 05225737)

## Storage:

---

Unlimited in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Store horizontally, without folds.

---

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations. and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from <https://eu.iko.com>.