IKO base Stick SBS F/SA 10 m

01570791

Description:

Underlayer composed of elastomer (SBS) bitumen and a glassgrid inlay. This underlay is finished with a thermofusible film on the upper surface and a self-adhesive lower surface.

Installation

Installation: fully self-adhesive with IKO pro SA primer (except on IKO enertherm ALU or MG against upstands and on uncoated EPS - use no primer)

Composition

Type of bitumen	Elastomeric
Upper surface finish	Thermofusible film
Inlay	Glassgrid 140 g/m²
Lower surface finish	Self-adhesive bitumen with anti-stick film

Technical characteristics:

Tensile strength L (EN 12311-1 MDV N/50 mm +/- 20%)	1250
Tensile strength T (EN 12311-1 MDV N/50 mm +/- 20%)	1200
Elongation L (EN 12311-1 MDV % +/- 15% abs.)	2
Elongation B (EN 12311-1 MDV % +/- 15% abs.)	2
Nail tear resistance(EN 12310-1 MDV N Only MF)	NPD
Flexibility at low temperature (EN 1109 MLV °C Surface/Bottom)	≤-10/-25
Flow temperature (EN 1110)	NPD
Shear resistance (EN 12317-1 MDV N/50 mm)	NPD
Dimensional stability (EN 1107-1 MLV)	≤ 0.3
Fire resistance	NPD
Vapour diffusion resistance (µd)	≥ 140 m
Root resistant (EN 13948)	-

Sizing and palletization:

Nominal thickness (mm)	2,8
Thickness tolerance (mm)	+/- 0,2
Length (m)	10
Width (m)	1
Width of overlap (cm)	8,0
Weight per roll(kg)	+/- 31,5
Number of rolls / pallet	24
Type of pallet	Euro-pallet

Always use a suitable pallet hoisting hook for vertical transport.

Certificates:

- Production ISO 9001 & 14001

IKO hereby certifies that this construction product complies with the provisions of the following European Directive(s) if installed in accordance with the system directions and installation rules set out in the documentation:

- Council Directive 89/106/EEC on Construction Products
- EN 13707

FPC certificate obtained from SGS Notified Body, registered under registration number 0958.

Certificate number: 0958-CPR-2009/1.