IKO roofgarden 4 APP T/F 7.5 m

01510321

Description:

Waterproofing membrane composed of plastomer (APP) bitumen with root resistant additives and a polyester-glass combination inlay. The upper surface is finished with sand slate and the lower surface is protected by a thermofusible film. This top layer can be applied in a single- or multi-layer system.

Installation

Installation: fully torched-on or loosely laid and ballasted

Composition

Type of bitumen	Plastomeric
Upper surface finish	Sand
Inlay	Polyester-glass combination 180 g/m²
Lower surface finish	Thermofusible film

Technical characteristics:

Tensile strength L (EN 12311-1 MDV N/50 mm +/- 20%)	700
Tensile strength T (EN 12311-1 MDV N/50 mm +/- 20%)	450
Elongation L (EN 12311-1 MDV % +/- 15% abs.)	20
Elongation B (EN 12311-1 MDV % +/- 15% abs.)	40
Nail tear resistance(EN 12310-1 MDV N Only MF)	≥ 150
Flexibility at low temperature (EN 1109 MLV °C Surface/Bottom)	≤-15
Flow temperature (EN 1110)	≥130
Shear resistance (EN 12317-1 MDV N/50 mm)	500
Dimensional stability (EN 1107-1 MLV)	≤ 0.3
Fire resistance	Froof
Vapour diffusion resistance (µd)	≥ 200 m
Root resistant (EN 13948)	OK

Sizing and palletization:

Nominal thickness (mm)	4,0
Thickness tolerance (mm)	+/- 0,2
Length (m)	7,5
Width (m)	1
Width of overlap (cm)	8,0
Weight per roll(kg)	+/- 38
Number of rolls / pallet	25
Type of pallet	1 x 1,2 m guarantee pallet

Always use a suitable pallet hoisting hook for vertical transport.

Certificates:

- CTG 028
- IAB 08/0316
- Production ISO 9001 & 14001

IKO hereby certifies that this construction product complies with the provisions of the following European Directive(s) if installed in accordance with the system directions and installation rules set out in the documentation:

- Council Directive 89/106/EEC on Construction Products
- EN 13707
- EN 13969

FPC certificate obtained from SGS Notified Body, registered under registration number 0958.

Certificate number: 0958-CPR-2009/1.