

## MS 210

### Description:

MS 210 is a low modulus single-component compound based on hybrid polymer.

### Use:

MS 210 is used for raising expansion and structural joints, dilatation joints between balcony and facade and joining between facade elements.

MS 210 is also used to glue Teknoprofil.

The adhesion of MS 210 to polyethylene, polypropylene, polycarbonate, PMMA, fluoropolymers, asphalt, bitumen, tar and oil materials can not be guaranteed.

### Colour:

Standard concrete grey, black and beige

### Packaging:

Concrete grey: 600mL sausage (item number 00051401)

Black: sausage of 600mL (item number 00051403)

Beige: sausage of 600mL (item number 00051402)

### Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

### Certificates:

ISO 9001 & 14001



### Technical characteristics:

Density	+/- 1,35 g/cm <sup>3</sup>
Hardness	+/- 25
Tensile strength	+/- 0,5 N/mm <sup>2</sup>
% Elongation	+/- 350%

### Application:

Air temperature	5°C - 40°C
Substrate temperature	5°C - 40°C
Product temperature	5°C - 30°C

### Cleaning of tools:

Immediately with soapy water

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from [www.ikoprotect.com](http://www.ikoprotect.com).