

# IKO Compound MN20

## Description:

Hot poured sealing compound made from elastomeric bitumen.

## Use:

- Ideal for filling wide and deep joints in bridgeheads (compound joints).
- Is used as a mixture with tinned 8/16 grit, which creates a smooth joint filler that can resist high indentation.
- Forms a bond between the transitions on concrete and asphalt roads.

## Characteristics:

- Has established elastic properties.
- High rigidity.
- Does not become fluid at high temperatures (+/- 70 °C).
- Maximum movement of the joint around 40 mm.
- Resists aggressive agents: resists to diluted acids and alkalis, but doesn't resist to hydrocarbon solvents and oils.

## Characteristics:

Colour	Black
Ring and boll EN 1427	95° C
Density	1
Cone penetration	46
Bullet penetration & rebound	71%
Needle penetration 25°C 100g 5s	42,8
Vertical efflux	0 mm
Vloeiweerstand EN13880-5	0
Elongation at -28°C	>= 50%
Form recovery at -28°C	100%

## Cleaning tools and stains:

Immediately, using white spirit.

## Implementation:

### Preparation of the substrate

- If the joint is milled out in 'ZOAB' (i.e. very open asphalt concrete), the edges must first be ground to prevent damage to this wearing course.
- The joint must be clean, dry and free from dirt.
- A galvanised metal sheet must be placed across the bottom of the joint. This must be secured at the side of the oncoming traffic.
- A layer of IKO CP primer Black must be applied.

### Melting and application of IKO Compound MN20

- The melting takes place in a melting pot with oil bath, fitted with a stirring rod and thermostat.
- Flow temperature: +/- 160 °C
- Critical temperature: +/- 200 °C
- Application temperature: +/- 180 °C
- In order to facilitate melting, we recommend filling the smelter to only one third of its capacity in the early stage.
- As soon as melting begins, the smelter can be completely filled
- Heat the tinned 8/16 grit to at least 180 °C, and apply to the joint.
- Pour the IKO Compound MN20 at a temperature of +/- 180 °C.
- If the depth of the joint exceeds 5 to 6 cm, work with several layers.
- Give the IKO compound MN20 the necessary time to enable the complete saturation of the joint.
- If possible, allow the joint to cool down completely before applying the final layer (cooling causes some shrinkage of IKO Compound MN20).
- Finish by spreading grit and rolling the surface.

### Storage:

Unlimited if stored dry

### Sizing and palletization:

- Bags of 23 kg (item number 02100160)
  - 44 bags per pallet / 1.012kg per pallet

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations. and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from <https://eu.iko.com>.