

IKO polyester Fleece 30

Characteristics:

- Non-woven polyester reinforcing fleece with a density of 30 g/m²
- Thickness control function when applying the first layer of the waterproofing membrane
- Can resist acids, the most common alkalis and bacteria
- Production ISO9001 & 14001

Use:

IKO polyester Fleece 30 is used as reinforcing fleece when applying the IKO hybritech MS Detail and IKO tanetech Detail liquid waterproofing system at angles, on cracks and when making a connection between two different flat materials.

Sizing and palletization:

10m x 0,25m roll (item number 02401830)

Storage:

Unlimited in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.



Technical characteristics:

Tensile strength MD	52 N/5cm
Tensile strength CD	61 N/5cm
% Elongation MD	28%
% Elongation CD	34%

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations. and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from <https://eu.iko.com>.