

IKO metatech Mortar L

Characteristics:

- Fast curing two-component mortar based on methacrylates
- Always mixed with IKO metatech Mortar P, that contains the required amount of catalyst (IKO perkadox).
- Production ISO9001 & 14001

Use:

IKO metatech Mortar (mix of IKO metatech Mortar L and P) is mainly used to prepare the substrate before IKO metatech systems are applied.

IKO metatech Mortar is used to repair important cracks and unevennesses >10 mm.

Sizing and palletization:

Metal tin with net weight of 1,75kg (item number 02414502)

Application:

We refer to our technical installation guidelines

Air temperature	-5°C - 35°C
Substrate temperature	3°C - 50°C
Product temperature	3°C - 30°C

The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

Substrate preparation:

We refer to our technical installation guidelines.

Mixing ratio and instructions:

First stir the content of the tin mechanically at the low-speed setting and add the IKO metatech Mortar P while stirring.

Cleaning of tools:

IKO metatech Cleaner

Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

Safety information:

We refer to our safety data sheet (MSDS), more specifically sections 2, 4, 5, 6, 7 and 8.



Technical characteristics:

Density	+/- 0,99 g/cm ³
Viscosity	+/- 25 sec (25°C, Flowcup 6mm)
Hardness	+/- 100

Curing time:

Pot life	+/- 15 min
Rain-proof	+/- 30 min
Can be walked on	+/- 45 min
Fully cured	+/- 3 h

Consumption rate:

2,2 kg IKO metatech Mortar/m² per mm layer thickness

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you



have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from <https://eu.iko.com>.