

IKO metatech Detail

Characteristics:

- Fast curing two-component coating based on methacrylates
- Flexible, also at very low temperatures
- Cures by adding the right amount of catalyst (IKO perkadox)
- Seamless and fully reinforced PMMA waterproofing
- Fast application wet-on-wet and fast curing
- Application also possible in hard-to-reach areas
- Enhanced sag resistance

Use:

IKO metatech Detail is used to realise a waterproof connection to complex roof details, like flashings, domes, roof lights, chimneys, air-conditioning nozzles, gutters and to balcony and car park details.

Thanks to its high viscosity, IKO metatech Detail doesn't flow down when applied on high flashings.

Sizing and palletization:

IKO metatech Detail

- Standard colours:
 - stone grey 7030: metal tin with net weight of 10kg (item number 02412410) and metal tin with net weight 5kg (item number 02412405)
 - pebble grey 7032 metal tin with net weight of 10kg (item number 02412510) and metal tin with net weight 5kg (item number 02412505)
- Project-specific colours are available. Please contact your IKO sales representative.

IKO perkadox: 100g plastic bag (item number 00095110)

IKO metatech Detail is delivered without IKO perkadox.

Application:

We refer to our technical installation guidelines.

Air temperature	5°C - 35°C
Substrate temperature	5°C - 40°C
Product temperature	5°C - 30°C

The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

Substrate preparation:

We refer to our technical installation guidelines.

Mixing ratio and instructions:

First stir the content of the tin mechanically at the low-speed setting. Add the IKO perkadox catalyst while stirring and mix mechanically and homogeneously at the low-speed setting during 2 minutes. Make sure that the product at the base and at the edge of the tin is properly mixed in.

The required amount of IKO perkadox for 10kg IKO metatech Detail depends on the temperature of the substrate:

+3°C till +5°C	0,3kg IKO perkadox	3%
+6°C till +15°C	0,2kg IKO perkadox	2%
+16°C till +40°C	0,1kg IKO perkadox	1%

- ETA-certificate 22/0465 according to EAD 030350-00-0402 with CE-marking: W3, S, P1 to P4, TL4, TH4
- BBA-certificate 24/7115 for roof applications
- External fire exposure resistance: Broof(t1) and Broof(t4)
- Root resistance according to EN13948
- Production ISO9001 & 14001



Technical characteristics:

Density	+/- 1,22 g/cm ³
Viscosity	+/- 50 dPas (25°C, 62,5 rpm, spindle 2)
Hardness	+/- 63 (Shore A 23°C)
Tensile strength	+/- 4,5 N/mm ²
% Elongation	+/- 240%

More information can be found in the DOP 02412410 010122.

Curing time:

Pot life	+/- 15 min
Rain-proof	+/- 30 min
Can be walked on	+/- 45 min
Fully cured	+/- 2 h

Consumption rate:

Min 3 kg/m²

Chemical resistance:

++ Highly resistant + Resistant (max 24h)

+/- Limited resistance (max 1h)

Acetic acid up to 30%	+
Ammonia up to 325%	+
Citric acid up to 50%	+
Formic acid up to 10%	+
Formic acid up to 30%	+/-
Household cleaners	++
Hydrochloric acid up to 10%	+/-
Lactic acid up to 30%	++
Lactic acid up to 10%	+



Cleaning of tools:

IKO metatech Cleaner

Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

Safety information:

We refer to our safety data sheet (MSDS), more specifically sections 2, 4, 5, 6, 7 and 8.

Nitric acid up to 10%	+/-
Phosphoric acid up to 20%	+/-
Phtalate	+
Saturated NaCl-solution	++
Sodium hypochlorite up to 5%	+

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from <https://eu.iko.com>.