IKO metatech Finish

Characteristics:

- Fast curing two-component coating based on methacrylates
- Cures by adding the appropriate amount of catalyst (IKO perkadox)
- High chemical resistance
- Production ISO9001 & 14001

Use:

IKO metatech Finish is used as broadcasting layer and sealer layer in the following liquid waterproofing systems:

- IKO metatech Balcony
- IKO metatech Car Park

On a car park, IKO metatech Finish is the hard layer that's in contact with the tires.

Sizing and palletization:

IKO metatech Finish:

- Standard colours:
  - stone grey 7030 metal tin with net weight of 10kg (item number 02412910)
  - pebble grey 7030 metal tin with net weight of 10kg (item number 02413310)
  - light grey 7035 metal tin with net weight of 10kg (item number 02412810)
  - traffic grey A 7042 metal tin with net weight of 10kg (item number 02413110)
  - traffic grey B 7043 metal tin with net weight of 10kg (item number 02412710)
  - transparent metal tin with net weight of 10kg (item number 02413010)
- Project-specific colours are available. Please contact your IKO sales representative.

IKO perkadox: 100 plastic bag (item number 00095110)

IKO metatech Finish is delivered without IKO perkadox.

Application:

We refer to our technical installation guidelines

Air temperature	5°C - 35°C
Substrate temperature	5°C - 40°C
Product temperature	5°C - 30°C

The temperature of the substrate shoud remain min. 3°C higher than the dew point during application and curing.

Substrate preparation:

We refer to our technical installation guidelines.

Mixing ratio and instructions:

First stir the content of the tin mechanically at the low-speed setting. Add the IKO perkadox catalyst while stirring and mix mechanically and homogeneously at the low-speed setting during 2 minutes. Make sure that the product at the base and at the edge of the tin is properly mixed in.

The required amount of IKO perkadox for 10kg IKO metatech Finish depends on the temperature of the substrate:



Technical characteristics:

Density	+/- 1,02 g/cm³
Viscosity	+/- 5 Pas (25°C, 1s-1)
Hardness	30-40 (Shore D 23°C)

Curing time:

Pot life	+/- 15 min
Rain-proof	+/- 30 min
Can be walked on	+/- 45 min
Fully cured	+/- 3 h

Consumption rate:

Depending on the application:

- Broadcasting layer min. 0,6 kg/m²
- Sealer 0,6-0,8 kg/m²

Chemical resistance:

++ Highly resistent + Resistent (max 24h)

+/- Limited resistence (max 1h)

Acetic acid up to 10%	++
Acetic acid up to 30%	+
Ammonia up to 25%	++
Citric acid up to 30%	++
Citric acid up to 50%	+
Diesel (fuel)	++
Formic acid up to 10%	++
Formic acid up to 30%	+/-
Householdcleaners	++
Hydrochloric acid up to 10%	+/-
Lactic acid up to 30%	++
Lactic acid up to 80%	+
Nitric acid up to 10%	++

+3°C tot +10°C	0,35kg IKO perkadox	3,5%
+11°C tot +20°C	0,25kg IKO perkadox	2,5%
+21°C tot +30°C	0,15kg IKO perkadox	1,5%
+31°C tot +40°C	0,1kg IKO perkadox	1%

Cleaning of tools:

IKO metatech Cleaner

Storage:

12 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid and the lever lock ring in the correct way and remove any product that might remain on the tin.

Safety information:

We refer to our safety data sheet (MSDS), more specificlayy sections 2, 4, 5, 6, 7 and 8.

Phosphoric acid up to 40%	++
Petrol (fuel)	++
Phtalate	+
Satutared NaCl-solution	++
Sodium hypochlorite up to 5%	++
White spirit	+

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations. and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from https://eu.iko.com.