IKO shield ALU3.5 T/MMP 8.0

01570300

Description:

Vapour barrier (indoor climate class IV) composed of elastomer bitumen (SBS) and a ALU-glassfleece combination inlay. The upper surface of this underlay is finished with a macro-perforated thermofusible film on the upper surface and the lower surface is protected by a thermofusible film.

Installation

Installation: fully torched-on or loosely laid and ballasted

Composition

Type of bitumen	Elastomeric
Upper surface finish	Macro-perforated thermofusible film (MMP)
Inlay	ALU-glassfleece combination 70 g/m²
Lower surface finish	Thermofusible film

Technical characteristics:

Tensile strength L (EN 12311-1 MDV N/50 mm +/- 20%)	400
Tensile strength T (EN 12311-1 MDV N/50 mm +/- 20%)	300
Elongation L (EN 12311-1 MDV % +/- 15% abs.)	5
Elongation B (EN 12311-1 MDV % +/- 15% abs.)	20
Nail tear resistance(EN 12310-1 MDV N Only MF)	NPD
Flexibility at low temperature (EN 1109 MLV °C Surface/Bottom)	≤-20
Flow temperature (EN 1110)	≥70
Shear resistance (EN 12317-1 MDV N/50 mm)	NPD
Dimensional stability (EN 1107-1 MLV)	NPD
Fire resistance	NPD
Vapour diffusion resistance (µd)	≥ 1500 m
Root resistant (EN 13948)	-

Sizing and palletization:

Nominal thickness (mm)	3,5
Thickness tolerance (mm)	+/- 0,2
Length (m)	8
Width (m)	1
Width of overlap (cm)	8,0
Weight per roll(kg)	+/- 38
Number of rolls / pallet	20
Type of pallet	Euro-pallet

Always use a suitable pallet hoisting hook for vertical transport.

Certificates:

- Production ISO 9001 & 14001

IKO hereby certifies that this construction product complies with the provisions of the following European Directive(s) if installed in accordance with the system directions and installation rules set out in the documentation:

- Council Directive 89/106/EEC on Construction Products
- EN 13707

FPC certificate obtained from SGS Notified Body, registered under registration number 0958.

Certificate number: 0958-CPR-2009/1.